

# Maxxam™ PPC-20G Nat

Polypropylene Copolymer

PolyOne Corporation

## Message:

PolyOne's Maxxam™ family of polypropylene- and polyethylene-based products covers a wide range of applications, markets and performance requirements. Standard grades are compounded with calcium carbonate, glass and talc to provide a desired balance of properties including stiffness, durability, impact resistance and heat resistance. Custom grades are available with features such as UV stabilizers, heat stabilizers, custom color, high impact, etc.

General Information			
Filler / Reinforcement	Filler,20% Filler by Weight Glass Fiber		
Additive	Impact Modifier		
Features	Copolymer		
	General Purpose		
	Impact Modified		
Uses	Automotive Applications		
	Construction Applications		
	Consumer Applications		
	General Purpose		
	Industrial Applications		
Appearance	Natural Color		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.03	g/cm <sup>3</sup>	ASTM D792
Specific Volume	0.972	cm <sup>3</sup> /g	ASTM D792
Melt Mass-Flow Rate (MFR) <sup>1</sup> (230°C/2.16 kg)	5.0	g/10 min	ASTM D1238
Molding Shrinkage - Flow	0.20 to 0.50	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength <sup>2</sup> (Yield)	50.0	MPa	ASTM D638
Tensile Elongation <sup>3</sup> (Break)	9.0	%	ASTM D638
Flexural Modulus	3030	MPa	ASTM D790
Flexural Strength	62.1	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, 3.18 mm, Injection Molded)	64	J/m	ASTM D256A
Thermal	Nominal Value	Unit	Test Method

Deflection Temperature Under Load (0.45 MPa, Unannealed, 3.18 mm)	152	°C	ASTM D648
Injection	Nominal Value	Unit	
Mold Temperature	16.0 to 50.0	°C	
NOTE			
1.	Procedure A		
2.	Type I, 51 mm/min		
3.	Type I, 51 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

