

# Paracril® X3675

Acrylonitrile Butadiene Rubber

INSA

## Message:

Description:

Excellent processability.

Highly crosslinked.

Hot polymerized.

Non staining nor discoloring stabilizer.

Applications:

pvc modification.

Blends with other paracril® polymers to improve extrusion or calendering performance.

General Information	
Features	Crosslinkable
	Good Processability
	Stain Resistant
Uses	Blending
Processing Method	Calendering
	Extrusion

Physical	Nominal Value	Unit	Test Method
Mooney Viscosity (ML 1+4, 100°C)	48 to 56	MU	ASTM D1646
ACN Content - Bound	36.5 to 39.5	wt%	Internal Method
Ash Content	< 1.0	wt%	ASTM D5667
Gel Content - in Mek	80.0 to 86.0	wt%	Internal Method
Stabilizer	> 1.0	wt%	Internal Method
Volatile Matter	< 1.0	wt%	ASTM D5668

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

## Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT