

# Sanren F850EBA (On-spec.)

Polypropylene Homopolymer  
SINOPEC Shanghai Petrochemical Co. Ltd.

Message:

The pellet product is colourless and in the shape of a cylinder with anti-blocking, high anti-static, high light transmittance, good mechanical performance and printability, stress-fracture resistant, excellent chemical stability, as well as fairly good heat-resistance.  
Scope of Application: Casting film

General Information			
Additive	Anti-caking agent		
	Antistatic property		
Features	High Light Transmission		
	High ESCR (Stress Cracking Resistance)		
	Excellent printability		
	Homopolymer		
	Anti-caking property		
	Antistatic property		
	Heat resistance, medium		
Uses	cast film		
Appearance	Colorless		
Forms	Particle		
Processing Method	Extrusion		
Physical	Nominal Value	Unit	Test Method
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	5.0 - 12	g/10 min	Internal method
Ash Content		%	
Fish Eye			
	400.0 μm	21.0 - 30.0	pcs/1520 cm <sup>2</sup>
	800.0 μm	3.10 - 5.00	pcs/1520 cm <sup>2</sup>
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	> 21.0	MPa	ASTM D638
Flexural Modulus	> 750	MPa	Internal method
Impact	Nominal Value	Unit	Test Method
Unnotched Izod Impact (23°C)	> 16	J/m	Internal method
Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature	> 125	°C	Internal method
Optical	Nominal Value	Unit	Test Method
Gloss	> 72		Internal method
Haze	< 2.2	%	Internal method

Yellowness Index	< 4.0	YI	Internal method
Additional Information	Nominal Value	Unit	

Cleanliness: 11-20 pieces/kg

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519  
Phone: +86 13424755533  
Email: sales@su-jiao.com  
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

