

Acrigel® LEP300

Polymethyl Methacrylate Acrylic

Unigel Plásticos

Message:

Medium flow rate, good impact resistance, good thermal resistance and good balance stiffness/impact.
Main applications: automotive lighting, appliances and technical parts.

General Information			
Features	Good Impact Resistance		
	Good Stiffness		
	Medium Flow		
	Medium Heat Resistance		
Uses	Appliances		
	Automotive Applications		
	Engineered Applications		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Melt Mass-Flow Rate (MFR) (230°C/3.8 kg)	3.8	g/10 min	ASTM D1238, ISO 1133
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (M-Scale)	90		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Break)	58.0	MPa	ASTM D638, ISO 527-2
Tensile Elongation (Break)	13	%	ASTM D638, ISO 527-2
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, 3.20 mm)	18	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
1.8 MPa, Unannealed, 3.20 mm	85.0	°C	ASTM D648
1.8 MPa, Unannealed	85.0	°C	ISO 75-2/A
Vicat Softening Temperature	106	°C	ISO 306/B50, ASTM D1525 1
Optical	Nominal Value	Unit	Test Method
Transmittance	92.0	%	ASTM D1003
NOTE			
1.	Rate A (50°C/h), Loading 2 (50 N)		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

