

# Arnite® TV4 230 S

Polybutylene Terephthalate

DSM Engineering Plastics

## Message:

Arnite® TV4 230 S is a Polybutylene Terephthalate (PBT) material filled with 15% glass fiber. It is available in Asia Pacific.

Important attributes of Arnite® TV4 230 S are:

Flame Rated

Flame Retardant

General Information			
UL YellowCard	E47960-240128		
Filler / Reinforcement	Glass Fiber, 15% Filler by Weight		
Additive	Flame Retardant		
Features	Flame Retardant		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Density	1.54	g/cm <sup>3</sup>	ISO 1183
Water Absorption			ISO 62
Saturation, 23°C	0.30	%	
Equilibrium, 23°C, 50% RH	0.15	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	7000	MPa	ISO 527-2
Tensile Stress (Break)	100	MPa	ISO 527-2
Tensile Strain (Break)	2.5	%	ISO 527-2
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	6.0	kJ/m <sup>2</sup>	ISO 179/1eA
Charpy Unnotched Impact Strength (23°C)	30	kJ/m <sup>2</sup>	ISO 179/1eU
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed	220	°C	ISO 75-2/B
1.8 MPa, Unannealed	200	°C	ISO 75-2/A
Melting Temperature <sup>1</sup>	225	°C	ISO 11357-3
CLTE			ISO 11359-2
Flow	5.0E-5	cm/cm/°C	
Transverse	8.0E-5	cm/cm/°C	
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	> 1.0E+15	ohms · cm	IEC 60093
Relative Permittivity			IEC 60250
100 Hz	3.10		
1 MHz	3.20		
Dissipation Factor			IEC 60250

100 Hz	1.0E-3		
1 MHz	0.013		
Flammability	Nominal Value	Unit	Test Method
Flammability Classification			IEC 60695-11-10, -20
1.50 mm	V-0		
0.750 mm	V-2		
Injection	Nominal Value	Unit	
Drying Temperature	100 to 120	°C	
Drying Time	3.0 to 12	hr	
Rear Temperature	230 to 240	°C	
Middle Temperature	235 to 250	°C	
Front Temperature	240 to 255	°C	
Nozzle Temperature	240 to 260	°C	
Processing (Melt) Temp	240 to 260	°C	
Mold Temperature	60.0 to 100	°C	
Injection Rate	Moderate-Fast		
Back Pressure	3.00 to 10.0	MPa	
Screw Compression Ratio	2.5:1.0		
NOTE			
1.	10°C/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

