

LUVOCOM® 65-8570/BL

Polypropylene Copolymer

Lehmann & Voss & Co.

Message:

LUVOCOM® 65-8570/BL is a polypropylene copolymer (PP Copoly) material, and the filler is glass fiber reinforced material. This product is available in Europe.

Typical application areas include:

engineering/industrial accessories

Tools

food contact applications

General Information			
Filler / Reinforcement	Glass fiber reinforced material		
Uses	Thin wall parts		
	Non-specific food applications		
	Engineering accessories		
	Machine/mechanical parts		
	Mold/Mold/Tool		
Appearance	Blue		
Physical	Nominal Value	Unit	Test Method
Density	1.05	g/cm ³	ISO 1183
Molding Shrinkage	0.80 - 1.4	%	DIN 16901
Water Absorption (23°C, 24 hr)	< 0.10	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	1700	MPa	ISO 527-2
Tensile Stress (Break)	22.0	MPa	ISO 527-2
Tensile Strain (Yield)	3.6	%	ISO 527-2
Flexural Modulus	1500	MPa	ISO 178
Flexural Stress	35.0	MPa	ISO 178
Flexural Strain at Flexural Strength	4.9	%	ISO 178
Maximum operating temperature-Short Term	110	°C	
Insulation Resistance	> 1.0E+12	ohms	IEC 60167
Impact	Nominal Value	Unit	Test Method
Charpy Unnotched Impact Strength (23°C)	35	kJ/m ²	ISO 179/1eU
Thermal	Nominal Value	Unit	Test Method
Continuous Use Temperature	80.0	°C	UL 746B
Vicat Softening Temperature	80.0	°C	ISO 306/A
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	> 1.0E+12	ohms	IEC 60093
Injection	Nominal Value	Unit	

Drying Temperature	70.0 - 95.0	°C
Drying Time	2.0 - 4.0	hr
Suggested Max Moisture	0.20	%
Rear Temperature	220 - 250	°C
Middle Temperature	220 - 250	°C
Front Temperature	230 - 250	°C
Nozzle Temperature	220 - 250	°C
Processing (Melt) Temp	230 - 260	°C
Mold Temperature	40.0 - 80.0	°C
Injection instructions		

General

In general LUVOCOM® can be processed on conventional injection moulding machines while observing the usual technical guidelines.

Any added fibrous materials or fillers may have an abrasive effect. In this case the cylinder and screw should be protected against wear as is usual in the processing of reinforced thermoplastic materials.

Lengthy dwell times for the melts in the cylinder should be avoided.

Lower the temperatures during interruptions!

Predrying (optional)

It is advisable to predry the granulate with a suitable dryer immediately before processing.

The granulate may absorb moisture from the air.

Delivery Form & Storage

Unless indicated otherwise, the material is delivered as 3mm-long pellets in sealed bags on pallets.

Preferably storage should be effected in dry and normally temperatured rooms

Additional Information

During processing, the moisture content should not exceed 0.2%. Moisture may lead to smearing and in extreme cases to foaming. Usually the material can be processed over a broad temperature range and can thus be adapted to a wide variety of processing conditions.

The processing notes provided merely represent a recommendation for general use. Due to the large variety of machines, geometries and volumes of parts, etc., it may be necessary to employ different settings according to the specific application.

Please contact us for further information.

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT