

Hifax CB 1128 G

Polypropylene Impact Copolymer

LyondellBasell Industries

Message:

"Hifax" CB 1128 G is a medium melt flow, 20% filled, UV stabilised, high impact polypropylene copolymer for injection moulding. It combines an excellent ductility and a good stiffness which makes it suitable for demanding impact absorbing applications. It is available in custom colour, pellet form.

General Information			
Filler / Reinforcement	Mineral,20% Filler by Weight		
Additive	UV Stabilizer		
Features	Ductile		
	Good Stiffness		
	Impact Copolymer		
	Medium Flow		
	Non-Toxic		
Uses	Automotive Applications		
	Automotive Exterior Parts		
	Automotive Exterior Trim		
Appearance	Colors Available		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.05	g/cm ³	ISO 1183/A
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	7.0	g/10 min	ISO 1133
Hardness	Nominal Value	Unit	Test Method
Shore Hardness (Shore D)	62		ISO 868
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Yield)	15.0	MPa	ISO 527-2
Tensile Strain (Break)	81	%	ISO 527-2
Flexural Modulus	1400	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact Strength			ISO 180/1A
-30°C	5.5	kJ/m ²	
-20°C	6.3	kJ/m ²	
23°C	No Break		
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (0.45 MPa, Unannealed)	92.0	°C	ISO 75-2/B

Vicat Softening Temperature			
--	115	°C	ISO 306/A50
--	40.0	°C	ISO 306/B50

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material


Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT