# SUNFROST® KD55JB

### Polyvinyl Chloride Elastomer

Mitsubishi Chemical Performance Polymers, Inc.

#### Message:

SUNFROST® KD55JB is a Polyvinyl Chloride Elastomer (PVC Elastomer) material. It is available in Asia Pacific for injection molding. Primary attribute of SUNFROST® KD55JB: Low Gloss.

Typical application of SUNFROST® KD55JB: Automotive

General Information	
Features	Low Gloss
Uses	Automotive Applications
	Automotive Interior Parts

Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.21	g/cm³	JIS K7112
Hardness	Nominal Value	Unit	Test Method
Shore Hardness (10 sec)	55		JIS K6253
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress (100% Strain)	3.50	MPa	JIS K6723
Tensile Stress (Break)	6.20	MPa	JIS K6723
Tensile Elongation (Break)	230	%	JIS K6723

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

