

# Cri-Line HFLT-615

Fluoroelastomer

Cri-Tech, Inc.

Message:

High fluorine tetrapolymers formulated for low temperature flexibility. HFLT compounds are excellent choices for fuel applications, including methanol-containing fuels, where low temperature flexibility is also essential. The LT compounds are designed for low temperature applications.

General Information		
Features	Low Temperature Flexibility	
Physical	Nominal Value	Unit
Specific Gravity	1.90	g/cm <sup>3</sup>
Hardness	Nominal Value	Unit
Durometer Hardness (Shore A)	60	
Elastomers	Nominal Value	Unit
Tensile Stress (100% Strain)	2.93	MPa
Tensile Strength	15.3	MPa
Tensile Elongation (Break)	240	%
Compression Set <sup>1</sup> (200°C, 22 hr)	5.0	%
NOTE		

1.
- Plied discs

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519  
Phone: +86 13424755533  
Email: sales@su-jiao.com  
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

