

GAPEX® RPP40DA

Polypropylene

Ferro Corporation

Message:

GAPEX® RPP40DA is a Polypropylene material filled with 40% glass fiber. It is available in Africa & Middle East, Asia Pacific, Europe, Latin America, or North America for injection molding.

General Information			
Filler / Reinforcement	Glass Fiber,40% Filler by Weight		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.22	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR)	2.0	g/10 min	ASTM D1238
Molding Shrinkage - Flow	0.30	%	ASTM D955
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore D)	82		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	55.2	MPa	ASTM D638
Tensile Elongation (Break)	2.0	%	ASTM D638
Flexural Modulus	6070	MPa	ASTM D790
Flexural Strength (Yield)	82.7	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, 3.18 mm)	64	J/m	ASTM D256
Unnotched Izod Impact (23°C, 3.18 mm)	110	J/m	ASTM D256
Gardner Impact	0.282	J	ASTM D3029
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed	146	°C	
1.8 MPa, Unannealed	141	°C	
Injection	Nominal Value	Unit	
Drying Temperature	71.1 to 82.2	°C	
Drying Time	2.0 to 4.0	hr	
Rear Temperature	221 to 238	°C	
Middle Temperature	227 to 243	°C	
Front Temperature	232 to 260	°C	
Nozzle Temperature	232 to 260	°C	
Processing (Melt) Temp	221 to 238	°C	
Mold Temperature	37.8 to 65.6	°C	
Injection Rate	Slow-Moderate		

Back Pressure	0.138 to 0.345	MPa
Cushion	5.08 to 12.7	mm

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

