

MAJORIS BW300 - 8229

Polypropylene

AD majoris

Message:

BW300 - 8229 is a 30% glass - filled polypropylene compound intended for injection moulding.

The product is available in both black (BW300 - 8229) and natural (BW300) but other colours can be provided on request.

BW300 - 8229 has been developed especially for the automotive applications and electrical components.

The good flowability of BW300 - 8229 makes it very easy to process even for complicated parts with long flow paths and it offers very high productivity with short cycle times. BW300 - 8229 is formulated to give an excellent surface finish with good scuff resistance.

APPLICATIONS

Products requiring good rigidity, low shrinkage, high dimensional stability can suitably be made from BW300 - 8229.

General Information			
Filler / Reinforcement	Glass fiber reinforced material, 30% filler by weight		
Features	Good dimensional stability		
	Recyclable materials		
	Workability, good		
	Fast molding cycle		
	Good liquidity		
	Scratch resistance		
	Low shrinkage		
	Excellent appearance		
Uses	Medium hardness		
	Electrical components		
Appearance	Application in Automobile Field		
	Black		
	Available colors		
Forms	Natural color		
	Particle		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Density	1.13	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	2.7	g/10 min	ISO 1133
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Yield)	45.0	MPa	ISO 527-2/50
Tensile Strain (Break)	24	%	ISO 527-2
Flexural Modulus ¹	2050	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method

Charpy Notched Impact Strength (23°C)	2.5	kJ/m ²	ISO 179/1eA
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	64.0	°C	ISO 75-2/A
Flammability	Nominal Value		Test Method
Flame Rating	HB		UL 94
Injection	Nominal Value	Unit	
Processing (Melt) Temp	210 - 260	°C	
Mold Temperature	30.0 - 50.0	°C	
Injection Rate	Moderate		
Injection instructions			
Holding pressure: 50 to 70% of the injection pressure			
NOTE			
1.	2.0 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

