

# Elastron® D D400.A30.B

Styrene Butadiene Styrene Block Copolymer

Elastron USA, Inc.

Message:

A soft, unfilled black SBS based thermoplastic elastomer (TPE) compound designed for injection molding applications.

Bondable to: PP, EVA, PE

| General Information           |                   |                   |             |
|-------------------------------|-------------------|-------------------|-------------|
| Features                      | Block Copolymer   |                   |             |
|                               | Bondability       |                   |             |
|                               | Soft              |                   |             |
| RoHS Compliance               | RoHS Compliant    |                   |             |
| Appearance                    | Black             |                   |             |
| Forms                         | Pellets           |                   |             |
| Processing Method             | Injection Molding |                   |             |
| Physical                      | Nominal Value     | Unit              | Test Method |
| Specific Gravity              | 0.900             | g/cm <sup>3</sup> | ASTM D792   |
| Molding Shrinkage             |                   |                   | ASTM D955   |
| Flow                          | 5.0               | %                 |             |
| Across Flow                   | 1.4               | %                 |             |
| Hardness                      | Nominal Value     | Unit              | Test Method |
| Durometer Hardness (Shore A)  | 30                |                   | ASTM D2240  |
| Elastomers                    | Nominal Value     | Unit              | Test Method |
| Tensile Stress                |                   |                   | ASTM D412   |
| 100% Strain                   | 0.300             | MPa               |             |
| 300% Strain                   | 0.600             | MPa               |             |
| Tensile Strength (Break)      | 3.60              | MPa               | ASTM D412   |
| Tensile Elongation (Break)    | 1800              | %                 | ASTM D412   |
| Tear Strength                 | 16.0              | kN/m              | ASTM D624   |
| Compression Set (23°C, 22 hr) | 18                | %                 | ASTM D395   |
| Injection                     | Nominal Value     | Unit              |             |
| Suggested Max Regrind         | 20                | %                 |             |
| Rear Temperature              | 140 to 150        | °C                |             |
| Middle Temperature            | 145 to 160        | °C                |             |
| Front Temperature             | 150 to 165        | °C                |             |
| Nozzle Temperature            | 165 to 185        | °C                |             |
| Mold Temperature              | 25.0 to 50.0      | °C                |             |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT