KW Plastics KWR101-150-M5 BLK

Medium Density Polyethylene

KW Plastics

Message:

Medium Density Polyethylene Post-Consumer Resin Extrusion

CHARACTERISTICS

Good impact resistance, good Flexibility, pre-colored black.

| General Information | | | |
|---------------------------------------|------------------------|----------|-----------------|
| Recycled Content | Yes | | |
| Features | Good Flexibility | | |
| | Good Impact Resistance | | |
| | Medium Density | | |
| | | | |
| RoHS Compliance | RoHS Compliant | | |
| Appearance | Black | | |
| Forms | Pellets | | |
| Processing Method | Extrusion | | |
| Physical | Nominal Value | Unit | Test Method |
| Specific Gravity | 0.955 | g/cm³ | ASTM D792 |
| Melt Mass-Flow Rate (MFR) (190°C/2.16 | | | |
| kg) | 0.55 | g/10 min | ASTM D1238 |
| Hardness | Nominal Value | Unit | Test Method |
| Durometer Hardness (Shore D) | 51 | | |
| Mechanical | Nominal Value | Unit | Test Method |
| Tensile Strength (Yield) | 23.4 | MPa | ASTM D638 |
| Flexural Modulus | 965 | MPa | ASTM D790 |
| Impact | Nominal Value | Unit | Test Method |
| Notched Izod Impact | No Break | | ASTM D256 |
| Additional Information | Nominal Value | Unit | Test Method |
| Polypropylene | < 2.0 | % | ASTM D5576 |
| Weight Loss on Heating (105°C) | < 0.10 | % | Internal Method |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

