

Lucalen A 2910 M

Ethylene Acrylic Acid Copolymer

LyondellBasell Industries

Message:

Lucalen A2910M is a natural adhesive low density polyethelene copolymer with a high thermal stability. Due to the acrylic acid/acrylate copolymer (E/A) content this grade offers excellent adhesion to polar materials (i.e. epoxy resin, steel, aluminium, etc.). It is design to be used by our customer in 2-layer anti corrosion coating as well as in wire & cable compounds. The material is available in pellet form.

General Information			
Features	Copolymer		
	Good thermal aging resistance		
	Good heat aging resistance		
	Good adhesion		
	Heat resistance, high		
	Thermal stability, good		
Uses	Protective coating		
	Pipeline coating		
	Coating application		
Forms	Particle		
Processing Method	Coating		
Physical	Nominal Value	Unit	Test Method
Density	0.927	g/cm ³	ISO 1183
Apparent Density	> 0.50	g/cm ³	ASTM D1895
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	7.0	g/10 min	ISO 1133
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore D)	38		ISO 868
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (23°C)	90.0	MPa	ISO 527-2
Tensile Stress (Yield, 23°C)	6.00	MPa	ISO 527-2
Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature	72.0	°C	ISO 306/A50
Melting Temperature	96.0	°C	
Additional Information	Nominal Value	Unit	Test Method
Comonomer AA	4.0	%	DIN 51451
Comonomer BA	7.0	%	DIN 51451
Unless specifically indicated, the grade mentioned is not suitable for applications in the pharmaceutical/medical sector. Not suitable for food contact.			
Extrusion	Nominal Value	Unit	
Melt Temperature	140 - 180	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

