

Borealis PP BC250MO

Polypropylene Impact Copolymer

Borealis AG

Message:

BC250MO is a very high impact polypropylene heterophasic copolymer intended for injection moulding. This grade is characterized by combination of good stiffness, good creep resistance and very high impact strength even at low temperatures. This grade features high impact strength, high thermal stability and very good processability. As all polypropylenes, this grade shows excellent stress-cracking and chemical resistances. This grade is mildly nucleated to maximize the mechanical stiffness. The additive formulation provides a smooth demoulding. Nucleation, good flow properties and high stiffness create a high potential for cycle time reduction. Its very good organoleptic properties allows this grade to be used with any masterbatch without discoloring problems.

General Information			
Additive	Nucleating Agent		
Features	Fast Molding Cycle		
	Good Chemical Resistance		
	Good Creep Resistance		
	Good Organoleptic Properties		
	Good Processability		
	Good Thermal Stability		
	High ESCR (Stress Crack Resist.)		
	High Impact Resistance		
	High Melt Stability		
	High Stiffness		
	Impact Copolymer		
	Low Temperature Impact Resistance		
	Nucleated		
Uses	Containers		
	Crates		
	Engineering Parts		
	Luggage		
	Support Trays		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	0.905	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	4.0	g/10 min	ISO 1133
Molding Shrinkage	1.0 to 2.0	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	1200	MPa	ISO 527-2/50
Tensile Stress (Yield)	23.0	MPa	ISO 527-2/50

Tensile Strain (Yield)	5.5	%	ISO 527-2/50
Flexural Modulus	1100	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
-20°C	7.5	kJ/m ²	
23°C	25	kJ/m ²	
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature ¹ (0.45 MPa, Unannealed)	80.0	°C	ISO 75-2/B
Injection	Nominal Value	Unit	
Processing (Melt) Temp	230 to 260	°C	
Mold Temperature	10.0 to 30.0	°C	
Injection Rate	Fast		
Holding Pressure	20.0 to 50.0	MPa	
NOTE			
1.	Injection molded specimen		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

