

ENVIROPLAS® ENV17-NC030

Polyether Imide

ENVIROPLAS®, Inc.

Message:

Injection Molding Grade, Transparent/Natural Amber Tint, Flame Retardant,
Excellent Thermal Performance, High Mechanical Strength and Stiffness, RoHS Compliant
NC030 = To Be Assigned 5 Digit Number Indicating Natural, Black, or Custom Color.
The ENV17 Series Products Are Available With Mold Release and/or UV Stabilizer.
Contact Enviropas Regarding UL Recognized Versions Of This Product.

General Information			
Additive	Flame Retardant		
Features	Flame Retardant		
	Good Thermal Stability		
	High Stiffness		
	High Strength		
RoHS Compliance	RoHS Compliant		
Appearance	Black		
	Clear Amber		
	Colors Available		
	Natural Color		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.27	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (337°C/6.6 kg)	18	g/10 min	ASTM D1238
Molding Shrinkage - Flow	0.50 to 0.70	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	109	MPa	ASTM D638
Tensile Elongation (Break)	55	%	ASTM D638
Flexural Modulus	3520	MPa	ASTM D790
Flexural Strength	163	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	32	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	199	°C	ASTM D648
Flammability	Nominal Value	Test Method	
Flame Rating			Internal Method
1.59 mm	V-0		

3.18 mm	5VA	
Injection	Nominal Value	Unit
Drying Temperature	149	°C
Drying Time	4.0 to 6.0	hr
Rear Temperature	332 to 399	°C
Middle Temperature	338 to 399	°C
Front Temperature	343 to 399	°C
Nozzle Temperature	343 to 399	°C
Mold Temperature	135 to 163	°C
Injection Rate	Moderate-Fast	
Back Pressure	0.345 to 0.689	MPa
Screw Speed	40 to 70	rpm

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

