

# VESTAMID® Care ML16

Polyamide 12  
Evonik Industries AG

Message:

VESTAMID® Care ML grades cover a range of polyamide 12 resins of different viscosity for processing via extrusion or injection molding. The VESTAMID® Care ML product range consists of unstabilized base resins as well as stabilized or reinforced compounds. VESTAMID® Care ML resins are characterized by several outstanding properties, such as high impact & notched impact resistance, dimensional stability, good sliding properties, high abrasion resistance and resistance against chemicals. Unfilled VESTAMID® Care ML grades are for example the materials of choice for catheters and tubings, where VESTAMID® Care ML materials meet even highest challenges in applications such as angioplasty balloon catheters. Typical areas of application for reinforced VESTAMID® Care ML grades include housing-parts, monitoring and imaging devices and durable medical equipment. Due to their low water uptake, filled VESTAMID® Care ML grades even resist steam autoclaving for more than 500 cycles. The advantages at a glance :

- High impact resistance
- High dimensional stability
- High chemical resistance
- Low sliding friction
- High toughness
- High abrasion resistance
- Easy processability & colorability

General Information			
Features	Biocompatible		
	Good Abrasion Resistance		
	Good Chemical Resistance		
	Good Colorability		
	Good Dimensional Stability		
	Good Impact Resistance		
	Good Processability		
	Good Toughness		
	Low Friction		
Uses	Medical Devices		
	Medical/Healthcare Applications		
	Tubing		
Agency Ratings	ISO 10993		
	USP 88		
	USP Class VI		
Processing Method	Extrusion		
	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density (23°C)	1.02	g/cm³	ISO 1183

Molding Shrinkage			ISO 294-4
Across Flow : 2.00 mm	1.1	%	
Flow : 2.00 mm	0.95	%	
Water Absorption			ISO 62
Saturation, 23°C	1.5	%	
Equilibrium, 23°C, 50% RH	0.70	%	
Viscosity Number	120	cm <sup>3</sup> /g	ISO 307
<b>Mechanical</b>	<b>Nominal Value</b>	<b>Unit</b>	<b>Test Method</b>
Tensile Modulus	1400	MPa	ISO 527-2
Tensile Stress (Yield, 23°C)	45.0	MPa	ISO 527-2/50
Tensile Strain (Yield, 23°C)	5.0	%	ISO 527-2/50
Nominal Tensile Strain at Break (23°C)	> 50	%	ISO 527-2/50
<b>Impact</b>	<b>Nominal Value</b>	<b>Unit</b>	<b>Test Method</b>
Charpy Notched Impact Strength			ISO 179/1eA
-30°C, Complete Break	5.0	kJ/m <sup>2</sup>	
23°C, Complete Break	5.0	kJ/m <sup>2</sup>	
Charpy Unnotched Impact Strength			ISO 179/1eU
-30°C	No Break		
23°C	No Break		
<b>Thermal</b>	<b>Nominal Value</b>	<b>Unit</b>	<b>Test Method</b>
Heat Deflection Temperature			
0.45 MPa, Unannealed	110	°C	ISO 75-2/B
1.8 MPa, Unannealed	50.0	°C	ISO 75-2/A
Vicat Softening Temperature			
--	170	°C	ISO 306/A
--	140	°C	ISO 306/B
Melting Temperature (DSC) <sup>1</sup>	178	°C	ISO 11357
CLTE - Flow (23 to 55°C)	1.5E-4	cm/cm/°C	ISO 11359-2
<b>Flammability</b>	<b>Nominal Value</b>		<b>Test Method</b>
Flame Rating			UL 94
1.60 mm	HB		
3.20 mm	HB		
<b>NOTE</b>			
1.	2nd Heating		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: [sales@su-jiao.com](mailto:sales@su-jiao.com)

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

