# Nymax<sup>™</sup> 1200 A UV White 205

## Polyamide 66

## PolyOne Corporation

#### Message:

Nymax of nylon 6/6 material ® 1200 blend series is "salt and pepper" pellet blend, including nylon resin, processing aid, performance modifier and color masterbatch.. According to different grade requirements, these materials have better melt processing, component properties and surface morphology, and are more economical substitutes for completely mixed products.

General Information				
Additive	Lubricant			
	UV stabilizer			
Features	Lubrication			
	General			
Uses	Industrial application Architectural application field Application in Automobile Field General Consumer goods application field			
Appearance	White			
Forms	Particle			
Processing Method	Injection molding			
Physical	Nominal Value	Unit	Test Method	
Specific Gravity	1.14	g/cm³	ASTM D792	
Molding Shrinkage - Flow	1.8 - 2.4	%	ASTM D955	
Water Absorption (24 hr, 3.18 mm)	1.2	%	ASTM D570	
Mechanical	Nominal Value	Unit	Test Method	
Tensile Modulus	2960	MPa	ASTM D638	
Tensile Strength <sup>1</sup>			ASTM D638	
Yield	79.3	MPa	ASTM D638	
Fracture	70.3	MPa	ASTM D638	
Tensile Elongation <sup>2</sup> (Yield)	30	%	ASTM D638	
Flexural Modulus	2900	MPa	ASTM D790	
Flexural Strength	117	MPa	ASTM D790	
Impact	Nominal Value	Unit	Test Method	
Notched Izod Impact - Across Flow (23°C, 3.18 mm, Injection Molded)	48	J/m	ASTM D256A	
Thermal	Nominal Value	Unit	Test Method	

Deflection Temperature Under Load (1.8			
MPa, Unannealed, 3.18 mm)	68.3	°C	ASTM D648
Melting Temperature	260	°C	ASTM D789
Additional Information			
Molded Test Bars: Dry as Molded			
Injection	Nominal Value	Unit	
Drying Temperature	82.2	°C	
Drying Time	4.0	hr	
Mold Temperature	60.0 - 107	°C	
NOTE			
1.	Type 1, 5.1 mm/min		
2.	Type 1, 5.1 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

# Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

