

# DINALON® PA 6.6 30% FV

Polyamide 66

Grupo Repol

## Message:

DINALON® PA 6.6 30% FV is a polyamide 66 (nylon 66) product, which contains 30% glass fiber reinforcement. It can be processed by injection molding and is available in Europe. The main characteristics are: flame retardant/rated flame.

General Information			
Filler / Reinforcement	Glass fiber reinforced material, 30% filler by weight		
Forms	Particle		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.36	g/cm <sup>3</sup>	ASTM D792
Molding Shrinkage - Flow	0.50	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	180	MPa	ASTM D638
Tensile Elongation (Break)	6.0	%	ASTM D638
Flexural Modulus	7500	MPa	ASTM D790
Flexural Strength	230	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Unnotched Izod Impact	150	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature	250	°C	ASTM D1525
Flammability	Nominal Value		Test Method
Flame Rating	HB		UL 94
Additional Information			
Glow Wire, UNE 20-672-83: 650°C Vicat Softening Temperature, ASTM D1525: >250°C DTUL, ASTM D648: 225°C			
Injection	Nominal Value	Unit	
Processing (Melt) Temp	280	°C	
Mold Temperature	85.0	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

## Recommended distributors for this material

### Susheng Import & Export Trading Co., Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT