

Sindustris PC GN2202FM

Polycarbonate

Sincerity Australia Pty Ltd.

Message:

Sindustris PC GN2202FM is a Polycarbonate (PC) material filled with 20% glass fiber. It is available in Asia Pacific for injection molding.

Important attributes of Sindustris PC GN2202FM are:

Flame Rated

Flame Retardant

Halogen Free

Heat Resistant

Typical applications include:

Housings

Electrical/Electronic Applications

General Information			
Filler / Reinforcement	Glass Fiber,20% Filler by Weight		
Additive	Flame Retardant		
Features	Flame Retardant		
	Halogen Free		
	High Heat Resistance		
Uses	Electrical Housing		
	Electrical/Electronic Applications		
	Housings		
UL File Number	E306922		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.35	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (300°C/1.2 kg)	7.0	g/10 min	ASTM D1238
Molding Shrinkage - Flow (3.20 mm)	0.10 to 0.30	%	ASTM D955
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	122		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ¹ (Yield, 3.20 mm)	108	MPa	ASTM D638
Tensile Elongation ² (Break, 3.20 mm)	3.0	%	ASTM D638
Flexural Modulus ³ (3.20 mm)	1.30	MPa	ASTM D790
Flexural Strength ⁴ (3.20 mm)	167	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, 3.20 mm)	110	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed, 6.40 mm)	142	°C	ASTM D648

RTI Elec	120	°C	UL 746
RTI Imp	90.0	°C	UL 746
RTI Str	105	°C	UL 746

Flammability	Nominal Value	Test Method
--------------	---------------	-------------

Flame Rating		UL 94
--------------	--	-------

1.50 mm	V-0	
---------	-----	--

	V-0	
--	-----	--

3.00 mm	5VA	
---------	-----	--

Injection	Nominal Value	Unit
-----------	---------------	------

Drying Temperature	100 to 120	°C
--------------------	------------	----

Drying Time	3.0 to 5.0	hr
-------------	------------	----

Suggested Max Moisture	0.020	%
------------------------	-------	---

Rear Temperature	270 to 300	°C
------------------	------------	----

Middle Temperature	280 to 310	°C
--------------------	------------	----

Front Temperature	290 to 330	°C
-------------------	------------	----

Nozzle Temperature	290 to 330	°C
--------------------	------------	----

Processing (Melt) Temp	300 to 340	°C
------------------------	------------	----

Mold Temperature	90.0 to 120	°C
------------------	-------------	----

Back Pressure	0.981 to 3.92	MPa
---------------	---------------	-----

Screw Speed	40 to 70	rpm
-------------	----------	-----

NOTE		
------	--	--

1.	50 mm/min	
----	-----------	--

2.	5.0 mm/min	
----	------------	--

3.	10 mm/min	
----	-----------	--

4.	1.3 mm/min	
----	------------	--

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT