

# Sindustris PP M1426

Polypropylene

Sincerity Australia Pty Ltd.

Message:

Sindustris PP M1426 is a Polypropylene material. It is available in Asia Pacific.

Typical applications include:

Automotive

Furniture

Household Applications

Housings

General Information			
Uses	Automotive Applications		
	Battery Cases		
	Household Goods		
	Outdoor Furnishings		
UL File Number	E306922		
Physical	Nominal Value	Unit	Test Method
Density	0.900	g/cm <sup>3</sup>	ASTM D1505
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	10	g/10 min	ASTM D1238
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	105		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength <sup>1</sup> (Yield)	27.5	MPa	ASTM D638
Tensile Elongation <sup>2</sup> (Break)	200	%	ASTM D638
Flexural Modulus	177	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	88	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	130	°C	ASTM D648
Vicat Softening Temperature	155	°C	ASTM D1525 <sup>3</sup>
NOTE			
1.	50 mm/min		
2.	50 mm/min		
3.	Loading 1 (10 N)		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

