ChronoPrene™ 25A

Thermoplastic Elastomer

CardioTech International, Inc.

Message:

ChronoPrene™ 25A is a Thermoplastic Elastomer (TPE) material. It is available in North America for extrusion or injection molding. Important attributes of ChronoPrene™ 25A are:

Chemical Resistant

Food Contact Acceptable

Good Aesthetics

Good Processability

High Flow

Typical application of ChronoPrene™ 25A: Food Contact Applications

| General Information | | | |
|------------------------------|--------------------------|-------|-------------|
| Additive | Plasticizer | | |
| Features | Food Contact Acceptable | | |
| | Good Chemical Resistance | | |
| | Good Moldability | | |
| | Good Surface Finish | | |
| | High Elasticity | | |
| | High Flow | | |
| | | | |
| Agency Ratings | FDA Unspecified Rating | | |
| Appearance | Translucent | | |
| Forms | Pellets | | |
| Processing Method | Extrusion | | |
| | Injection Molding | | |
| | | | |
| Physical | Nominal Value | Unit | Test Method |
| Specific Gravity | 0.868 | g/cm³ | ASTM D792 |
| Hardness | Nominal Value | Unit | Test Method |
| Durometer Hardness (Shore A) | 25 | | ASTM D2240 |
| Elastomers | Nominal Value | Unit | Test Method |
| Tensile Strength (Yield) | 4.14 | МРа | ASTM D412 |
| Tensile Elongation (Yield) | 600 | % | ASTM D412 |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

