KW Plastics KW 622

Polypropylene Copolymer

KW Plastics

Message:

Copolymer Polypropylene Post-Consumer Resin Injection Molding CHARACTERISTICS

Good impact resistance. Available as mixed color and pre-colored black.

| General Information | | | |
|--------------------------------------|------------------------|----------|-------------|
| Recycled Content | Yes | | |
| Features | Copolymer | | |
| | Good Impact Resistance | | |
| | | | |
| RoHS Compliance | RoHS Compliant | | |
| Appearance | Black | | |
| | Colors Available | | |
| | | | |
| Forms | Pellets | | |
| Processing Method | Injection Molding | | |
| Physical | Nominal Value | Unit | Test Method |
| Specific Gravity | 0.910 | g/cm³ | ASTM D792 |
| Melt Mass-Flow Rate (MFR) (230°C/2.1 | 6 | | |
| kg) | 11 | g/10 min | ASTM D1238 |
| Mechanical | Nominal Value | Unit | Test Method |
| Tensile Strength (Yield) | 22.8 | МРа | ASTM D638 |
| Tensile Elongation (Yield) | 11 | % | ASTM D638 |
| Flexural Modulus | 917 | MPa | ASTM D790 |
| Impact | Nominal Value | Unit | Test Method |
| Notched Izod Impact | 110 | J/m | ASTM D256 |
| Thermal | Nominal Value | Unit | Test Method |
| Deflection Temperature Under Load (1 | | | |
| MPa, Unannealed) | 80.0 | °C | ASTM D648 |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

