

Stat-Tech™ AS-1000 AS

Acrylonitrile Butadiene Styrene

PolyOne Corporation

Message:

Stat-Tech™ Electrically Conductive Compounds are specifically engineered to provide anti-static, ESD and RFI/EMI shielding performance for critical electronic equipment applications. These compounds combine the performance of select engineering resins with reinforcing additives such as carbon powder, carbon fiber, nickel-coated carbon fiber and stainless steel fiber, for low to high levels of conductivity depending upon application requirements.

| General Information | | | |
|---|------------------------------------|-------------------|-------------|
| Features | Antistatic | | |
| | Non-Sloughing | | |
| Uses | Aerospace Applications | | |
| | Automotive Electronics | | |
| | Business Equipment | | |
| | Computer Components | | |
| | Connectors | | |
| | Electrical Housing | | |
| | Electrical/Electronic Applications | | |
| | Housings | | |
| RoHS Compliance | RoHS Compliant | | |
| Forms | Pellets | | |
| Processing Method | Injection Molding | | |
| Physical | Nominal Value | Unit | Test Method |
| Specific Gravity | 1.06 | g/cm ³ | ASTM D792 |
| Melt Mass-Flow Rate (MFR) | 8.5 | g/10 min | ASTM D1238 |
| Molding Shrinkage | | | ASTM D955 |
| Flow | 0.40 to 0.60 | % | |
| Across Flow | 0.40 to 0.60 | % | |
| Mechanical | Nominal Value | Unit | Test Method |
| Tensile Modulus ¹ | 1940 | MPa | ASTM D638 |
| Tensile Strength (Break) | 35.0 | MPa | ASTM D638 |
| Tensile Elongation ² (Break) | 12 | % | ASTM D638 |
| Flexural Modulus | 20700 | MPa | ASTM D790 |
| Flexural Strength | 59.8 | MPa | ASTM D790 |
| Impact | Nominal Value | Unit | Test Method |
| Notched Izod Impact (23°C, 3.18 mm, Injection Molded) | 210 | J/m | ASTM D256A |
| Thermal | Nominal Value | Unit | Test Method |
| Deflection Temperature Under Load | | | ASTM D648 |

| 0.45 MPa, Unannealed, 6.35 mm | 87.0 | °C | |
|--|--------------------|---------|-------------|
| 1.8 MPa, Unannealed, 6.35 mm | 74.0 | °C | |
| Electrical | Nominal Value | Unit | Test Method |
| Surface Resistivity | 1.0E+11 to 1.0E+12 | ohms | ASTM D257 |
| Volume Resistivity | 1.0E+11 to 1.0E+12 | ohms·cm | ASTM D257 |
| Static Decay | | | |
| (Mil-B-81705C), 12% RH, 5000 kV to 50 kV | 0.3 | sec | |
| (Mil-B-81705C), 50% RH, 5000 kV to 50 kV | 0.1 | sec | |
| Injection | Nominal Value | Unit | |
| Processing (Melt) Temp | 227 to 238 | °C | |
| NOTE | | | |
| 1. | Type I, 5.1 mm/min | | |
| 2. | Type I, 5.1 mm/min | | |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT