

Fortron® 4184L6

Polyphenylene Sulfide

Celanese Corporation

Message:

Fortron 4184L6 is an easier flow version of Fortron 4184L4. It offers similar characteristics to the 4184L4. This grade is especially used for thin walled parts requiring long flow lengths, stiffness and dimensional control. Applications made of this grade are typically electronic components.

General Information			
UL YellowCard	E107854-237743		
Filler / Reinforcement	Glass \mineral, 53% filler by weight		
Features	Good dimensional stability		
	Rigid, good		
	Good liquidity		
Uses	Thin wall parts		
	Electrical/Electronic Applications		
RoHS Compliance	Contact manufacturer		
Multi-Point Data	Isochronous Stress vs. Strain (ISO 11403-1)		
	Isothermal Stress vs. Strain (ISO 11403-1)		

Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.80	g/cm ³	ASTM D792, ISO 1183
Specific Volume	0.556	cm ³ /g	ASTM D792
Specific Heat Capacity of Melt	1500	J/kg/°C	Internal method
Molding Shrinkage			
Flow	0.10 - 0.30	%	ASTM D955
Transverse flow	0.40 - 0.60	%	ASTM D955
Vertical flow direction	0.40 - 0.70	%	ISO 294-4
Flow direction	0.30 - 0.60	%	ISO 294-4
Water Absorption (Saturation, 23°C)	0.020	%	ISO 62

Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness			
Class m	100		ASTM D785
M scale	100		ISO 2039-2

Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	16600	MPa	ISO 527-2/1A/1
Tensile Strength			
Fracture, 23°C	165	MPa	ASTM D638
Fracture	165	MPa	ISO 527-2/1A/5

Tensile Elongation			
Fracture, 23°C	1.5	%	ASTM D638
Fracture	1.4	%	ISO 527-2/1A/5
Flexural Modulus (23°C)	16200	MPa	ISO 178
Flexural Stress ¹	250	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
-30°C	7.0	kJ/m ²	ISO 179/1eA
23°C	7.0	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength			ISO 179/1eU
-30°C	29	kJ/m ²	ISO 179/1eU
23°C	29	kJ/m ²	ISO 179/1eU
Notched Izod Impact			ISO 180/1A
-30°C	7.0	kJ/m ²	ISO 180/1A
23°C	7.0	kJ/m ²	ISO 180/1A
Unnotched Izod Impact Strength (23°C)	27	kJ/m ²	ISO 180/1U
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
0.45 MPa, annealed	280	°C	ASTM D648
1.8 MPa, not annealed	265	°C	ASTM D648
1.8 MPa, not annealed	270	°C	ISO 75-2/A
8.0 MPa, not annealed	215	°C	ISO 75-2/C
Glass Transition Temperature ²	90.0	°C	ISO 11357-2
Melting Temperature ³	280	°C	ISO 11357-3
Linear thermal expansion coefficient			ISO 11359-2
Flow	2.4E-5	cm/cm/°C	ISO 11359-2
Lateral	3.2E-5	cm/cm/°C	ISO 11359-2
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	> 1.0E+15	ohms	IEC 60093
Volume Resistivity			
--	1.0E+16	ohms · cm	ASTM D257
--	> 1.0E+15	ohms · cm	IEC 60093
Dielectric Strength	27	kV/mm	IEC 60243-1
Dielectric Constant			
1 kHz	3.80		ASTM D150
1 MHz	3.80		ASTM D150
1 MHz	4.70		IEC 60250
Dissipation Factor			
1 kHz	1.0E-3		ASTM D150
1 MHz	8.0E-4		ASTM D150
1 MHz	2.0E-3		IEC 60250
Arc Resistance	156	sec	ASTM D495

Comparative Tracking Index	150	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
0.750 mm	V-0		UL 94
1.50 mm	V-0		UL 94
Injection	Nominal Value	Unit	
Drying Temperature	130 - 140	°C	
Drying Time	3.0 - 4.0	hr	
Suggested Max Moisture	0.020	%	
Hopper Temperature	20.0 - 30.0	°C	
Rear Temperature	290 - 300	°C	
Middle Temperature	310 - 320	°C	
Front Temperature	330 - 340	°C	
Nozzle Temperature	310 - 330	°C	
Processing (Melt) Temp	330 - 340	°C	
Mold Temperature	140 - 160	°C	
Injection Pressure	50.0 - 100	MPa	
Injection Rate	Fast		
Holding Pressure	30.0 - 70.0	MPa	
Back Pressure	0.00 - 3.00	MPa	
Injection instructions			
Manifold Temperature: 330 to 340°CZone 4 Temperature: 330 to 340°CFeed Temperature: 60 to 80°C			
NOTE			
1.	Break		
2.	10°C/min		
3.	10°C/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT