Hanwha Total PP BJ750

Polypropylene Impact Copolymer

HANWHA TOTAL PETROCHEMICALS Co., Ltd.

Message:

BJ750 is for injection molding application. STC impact copolymer shows an easy processability and an excellent stiffness combined with good impact strength & appearance.

Characteristics & Applications

Excellent balance between stiffness and impact strength

Good appearance (gas mark and void free, high gloss)

Good processability and productivity

Applications : Large E&E articles: Dish Washer Tub, W/M, & TWIM

General Information				
Features	Food Contact Acceptable			
	Good Impact Resistance			
	Good Processability			
	High Gloss			
	High Stiffness			
	Impact Copolymer			
Uses	Appliances			
	Electrical/Electronic Applications			
	Thin-walled Parts			
Agency Ratings	FDA 21 CFR 177.1520			
Forms	Pellets			
Processing Method	Injection Molding			
Physical	Nominal Value	Unit	Test Method	
Density	0.910	g/cm³	ASTM D1505	
Melt Mass-Flow Rate (MFR) (230°C/2.16				
kg)	28	g/10 min	ASTM D1238	
Hardness	Nominal Value	Unit	Test Method	
Rockwell Hardness (R-Scale)	90		ASTM D785	
Mechanical	Nominal Value	Unit	Test Method	
Tensile Strength (Yield)	28.4	MPa	ASTM D638	
Tensile Elongation (Break)	> 100	%	ASTM D638	
Flexural Modulus	1520	MPa	ASTM D790	
Impact	Nominal Value	Unit	Test Method	
Notched Izod Impact			ASTM D256	
-20°C	39	J/m		
0°C	49	J/m		
23°C	78	J/m		

Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature	120	°C	ASTM D648

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

