

SUPRAN® PP1330

Polypropylene

SAMBARK

Message:

SUPRAN® is injection-moldable Long Fiber Reinforced Thermoplastics(LFT), PP1330 is Polypropylene reinforced with 30wt% long glass fibers. Parts molded of SUPRAN ® have outstanding mechanical properties such as high strength, stiffness, impact and creep resistance and low warpage combined with high heat deflection. SUPRAN ® PP1330 is suitable for structural parts in automotive and industrial application.

General Information			
UL YellowCard	E230962-230053		
Filler / Reinforcement	Long Glass Fiber,30% Filler by Weight		
Features	Good Creep Resistance		
	High Impact Resistance		
	High Stiffness		
	High Strength		
	Low Warpage		
Uses	Automotive Applications		
	Industrial Applications		
	Structural Parts		
RoHS Compliance	RoHS Compliant		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.11	g/cm ³	ASTM D792
Molding Shrinkage - Flow	0.40	%	ASTM D955
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	108		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	113	MPa	ASTM D638
Tensile Elongation (Break)	2.7	%	ASTM D638
Flexural Modulus	6570	MPa	ASTM D790
Flexural Strength	157	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			ASTM D256
-30°C	210	J/m	
23°C	200	J/m	
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	161	°C	ASTM D648
Injection	Nominal Value	Unit	

Rear Temperature	220 to 230	°C
Middle Temperature	220 to 230	°C
Front Temperature	220 to 230	°C
Mold Temperature	40.0 to 70.0	°C

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

