

Greene FKM 761

Fluoroelastomer

Greene, Tweed & Co.

Message:

Greene FKM 761 is a Fluoroelastomer product. It is available in North America.

General Information			
Appearance	Black		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.80	g/cm ³	ASTM D297
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (M-Scale)	75		ASTM D785
Durometer Hardness (Shore A)	77		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Coefficient of Friction ¹			ASTM D1894
vs. Itself - Dynamic	1.1		
vs. Itself - Static	1.2		
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress			ASTM D412
50% Strain	2.48	MPa	
100% Strain	6.89	MPa	
Tensile Strength (Break)	16.0	MPa	ASTM D412
Tensile Elongation (Break)	190	%	ASTM D412
Compression Set ²			ASTM D395
24°C, 70 hr	7.0	%	
175°C, 166 hr	24	%	
200°C, 22 hr	12	%	
Aging	Nominal Value	Unit	Test Method
Change in Tensile Strength in Air (276°C, 70 hr)	-25	%	ASTM D573
Change in Ultimate Elongation in Air (276°C, 70 hr)	-8.0	%	ASTM D573
Change in Durometer Hardness in Air (Shore A, 276°C, 70 hr)	-1.0		ASTM D573
Change in Tensile Strength			ASTM D471
24°C, 70 hr, in Reference Fuel B	-12	%	
200°C, 70 hr, in Reference Oil 300	-12	%	
Change in Ultimate Elongation			ASTM D471
24°C, 70 hr, in Reference Fuel B	2.0	%	
200°C, 70 hr, in Reference Oil 300	13	%	

Change in Durometer Hardness			ASTM D471
Shore A, 24°C, 70 hr, in Reference Fuel B	-2.0		
Shore A, 200°C, 70 hr, in Reference Oil 300	-6.0		
Change in Mass (276°C, 70 hr, in Air)	-8.0	%	ASTM D471
Change in Volume			ASTM D471
24°C, 70 hr, in Reference Fuel B	2.3	%	
200°C, 70 hr, in Reference Oil 300	15	%	
Thermal	Nominal Value	Unit	Test Method
CLTE - Flow	2.2E-4	cm/cm/°C	ASTM E228
Service Temperature	-40 to 232	°C	
Rubber Classification	FKM		ASTM D1418
NOTE			
1.	Method C		
2.	25% Deflection		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

