

# SUMILITE® PL-1622

Phenolic

Sumitomo Bakelite Co., Ltd.

Message:

SUMILITE®PL-1622 is a phenolic (Phenolic) product, which contains cotton filler. It is available in North America. Typical application areas are: coating applications.

General Information			
Filler / Reinforcement	Cotton filler		
Uses	Laminate		
Forms	Particle		
Hardness	Nominal Value	Test Method	
Rockwell Hardness (M-Scale)	105	ASTM D785	
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (1.20 mm)	61	J/m	ASTM D256
Additional Information			

Flexural Strength @ Yield, ASTM D790, 1.2 mm, Machine MD: 160 MPaFlexural Strength @ Yield, ASTM D790, 1.2 mm, TD: 130 MPa

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

