

Huaфон JF-W-HE6015

Polyurethane

Huaфон Group Co., Ltd.

Message:

General Wet Process PU Resin with Hydrolysis Resistance

Characteristics

Special resin for embossing, super soft type, 24 hours hydrolysis resistance, high peeling strength, good film thickness, good elasticity, good smoothness.

Applications

Garments, Boots

| General Information | | |
|-------------------------------|----------------------|------|
| Features | High Elasticity | |
| | Hydrolysis Resistant | |
| | Soft | |
| Uses | Footwear | |
| | Textile Applications | |
| Additional Information | Nominal Value | Unit |
| Solvents | DMF | |
| Uncured Properties | Nominal Value | Unit |
| Solids Content | 29 to 31 | % |
| Viscosity (25°C) | 160 to 260 | Pa·s |
| Cured Properties | Nominal Value | Unit |
| Tensile Modulus (100% Secant) | 2.00 to 3.00 | MPa |
| Tensile Strength | > 8.00 | MPa |
| Tensile Elongation at Break | > 450 | % |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co., Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT