

Glastic® 2450-15

Thermoset Polyester

Glastic Corporation

Message:

Glastic 2450-15 is a standoff insulator that is molded of UL recognized flame resistant fiberglass-reinforced thermoset polyester molding compound. Glastic 2450-15 features shatter resistance and closer height tolerances than commonly available in porcelain insulators. Moisture and heat resistance properties of Glastic 2450-15 are higher than those of conventional plastic insulators. Glastic 2450-15 should not be used upside down if there is a possibility of the center hole being filled with water.

General Information			
Filler / Reinforcement	Glass fiber reinforced material		
Features	mildew proof		
	Heat resistance, high		
	Flame retardancy		
Uses	Isolated insulator		
UL File Number	E23525		
	E81713		
Forms	Particle		
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	34.5	MPa	ASTM D638
Compressive Strength	138	MPa	ASTM D695
Electrical	Nominal Value	Unit	Test Method
Arc Resistance	180	sec	ASTM D495
Flammability	Nominal Value	Unit	Test Method
Flame Rating	V-0		UL 94
Additional Information			

Cantilever Strength: 10000in/lbsTorque Strength: 285 ft/lbsHeight Tolerance: .015Creep Resistance: 7 inchDry Hi-Pot, NEMA Specs: 36000 VoltsDew Hi-Pot, NEMA Specs: 26000 VoltsImpulse, 1.5 x 40 wave: 95000Track Resistance: 600 min

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT