

VITAMIDE® BF10

Polyamide 6
A. Schulman Europe

Message:

VITAMIDE® BF10 is a Polyamide 6 (Nylon 6) material. It is available in Africa & Middle East, Asia Pacific, Europe, Latin America, or North America for injection molding.

Important attributes of VITAMIDE® BF10 are:

Flame Rated
RoHS Compliant
Flame Retardant

Typical applications include:

Electrical/Electronic Applications
Engineering/Industrial Parts

General Information			
UL YellowCard	E132739-546975		
Additive	Flame Retardant		
Features	Flame Retardant		
Uses	Connectors		
	Electrical Parts		
	Plugs		
RoHS Compliance	RoHS Compliant		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.13	g/cm ³	ISO 1183
Molding Shrinkage	1.5	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Yield)	75.0	MPa	ISO 527-2
Tensile Strain (Break)	75	%	ISO 527-2
Flexural Modulus	2600	MPa	ISO 178
Flexural Stress	95.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact Strength	6.0	kJ/m ²	ISO 180
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed	185	°C	ISO 75-2/B
1.8 MPa, Unannealed	60.0	°C	ISO 75-2/A
Melting Temperature (DSC)	221	°C	ISO 3146
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+15	ohms	IEC 60093
Electric Strength (2.00 mm)	21	kV/mm	IEC 60243-1
Comparative Tracking Index (Solution A)	600	V	IEC 60112

Flammability	Nominal Value	Unit	Test Method
Flame Rating	V-2		UL 94
Glow Wire Ignition Temperature	750	°C	IEC 60695-2-13

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

