BP ABS 3333 R BLK

Acrylonitrile Butadiene Styrene

Buckeye Polymers, Inc.

Message:

Product Information: Our BP ABS 3333 R Blk offers better than average impact while providing good melt flow characteristics in an affordably priced material. The values listed below are for minimum.values and Buckeye Polymers always guarantees that the material will surpass the requirements listed. Features:

Good Impact and melt flow

Can be packaged in new plain white containers or shipped in bulk

A balance mixture or recycled content and virgin resins to achieve optimal physical property performance yet meeting aggressive price points.

General Information			
Features	Good Flow		
	Good Impact Resistance		
	Recyclable Material		
Appearance	Black		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.04	g/cm³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/3.8 kg)	3.0	g/10 min	ASTM D1238
Color - ^E	1.5		Internal Method
Mechanical	Nominal Value	Unit	Test Method
Flexural Modulus (23°C)	> 2280	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	> 160	J/m	ASTM D256

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

