

# MAJ'ECO EG368LA

Biodegradable Polymers

AD majoris

## Message:

MAJ'ECO EG368LA is a glass fibre reinforced Biopolymer compound intended for injection moulding.

MAJ'ECO EG368LA has been developed especially for demanding applications in various engineering sectors.

MAJ'ECO EG368LA has high rigidity, good dimensional stability.

## APPLICATIONS

Electrical appliances

Exterior parts

Technical components

Sports leisure

General Information			
Filler / Reinforcement	Glass fiber reinforced material, 35% filler by weight		
Features	Good dimensional stability		
	Rigidity, high		
	Updatable resources		
	Recyclable materials		
Uses	Electrical/Electronic Applications		
	Electrical appliances		
	Outdoor application		
	Sporting goods		
Forms	Particle		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Density	1.51	g/cm <sup>3</sup>	ISO 1183
Melt Mass-Flow Rate (MFR) (190°C/5.0 kg)	16	g/10 min	ISO 1133
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	10600	MPa	ISO 527-2/1
Tensile Stress (Break)	104	MPa	ISO 527-2/50
Tensile Strain (Break)	1.7	%	ISO 527-2/50
Flexural Modulus <sup>1</sup>	9150	MPa	ISO 178
Flexural Stress <sup>2</sup>	180	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	9.0	kJ/m <sup>2</sup>	ISO 179/1eA
Charpy Unnotched Impact Strength (23°C)	35	kJ/m <sup>2</sup>	ISO 179/1eU
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, not annealed	116	°C	ISO 75-2/B

1.8 MPa, not annealed	59.0	°C	ISO 75-2/A
Flammability	Nominal Value		Test Method
Flame Rating	HB		UL 94
Injection	Nominal Value	Unit	
Drying Temperature	50.0	°C	
Drying Time	4.0	hr	
Processing (Melt) Temp	150 - 190	°C	
Mold Temperature	30.0 - 50.0	°C	
Injection Rate	Moderate		
Injection instructions			
Holding pressure: 50 to 70% of the injection pressure			
NOTE			
1.	2.0 mm/min		
2.	50 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

