

Beetafin® L9032

Polyurethane (Polyester based)

BIP (Oldbury) Limited

Message:

Beetafin® L9032 is a Polyurethane (Polyester based) (PUR-Ester) product. It is available in Europe.

General Information		
Physical	Nominal Value	Unit
pH	8.5	
Solids Content	35	%
Solvent Content	4% DPGDME	
Konig Hardness	1.6	min
Films	Nominal Value	Unit
Secant Modulus - 100%, MD	8.40	MPa
Tensile Strength	32.0	MPa
Tensile Elongation - MD (Break)	550	%
Thermal	Nominal Value	Unit
Vicat Softening Temperature	165	°C
Uncured Properties	Nominal Value	Unit
Viscosity	0.45	Pa · s

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

