

VENYL SW502H - 8229

Polyamide 6

AD majoris

Message:

VENYL SW502H - 8229 is a 50% glass fiber filled polyamide 6 medium viscosity intended for Injection moulding.

APPLICATIONS

VENYL SW502H - 8229 has been developed especially for very demanding applications in automotive industry and electrical parts.

VENYL SW502H - 8229 is available in both black and natural (VENYL SW502H) but other colours can be provided on request.

General Information			
Filler / Reinforcement	Glass Fiber,50% Filler by Weight		
Features	Medium Viscosity		
	Recyclable Material		
Uses	Automotive Applications		
	Electrical Parts		
Appearance	Black		
	Colors Available		
	Natural Color		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.56	g/cm ³	ISO 1183
Molding Shrinkage	0.20 to 0.40	%	
Water Absorption (Equilibrium, 23°C, 50% RH)	1.5	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	15500	MPa	ISO 527-2
Tensile Stress (Break)	185	MPa	ISO 527-2
Tensile Strain (Break)	3.0	%	ISO 527-2
Flexural Modulus	12500	MPa	ISO 178
Flexural Stress	285	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength	18	kJ/m ²	ISO 179
Charpy Unnotched Impact Strength	75	kJ/m ²	ISO 179
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed	220	°C	ISO 75-2/B
1.8 MPa, Unannealed	212	°C	ISO 75-2/A

Melting Temperature (DSC)	220	°C	ISO 3146
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+13	ohms	DIN 53482
Volume Resistivity	1.0E+14	ohms·cm	DIN 53482
Flammability	Nominal Value	Unit	Test Method
Flame Rating (1.60 mm)	HB		UL 94
Injection	Nominal Value	Unit	
Drying Temperature	100	°C	
Drying Time	4.0	hr	
Rear Temperature	265 to 280	°C	
Middle Temperature	255 to 270	°C	
Front Temperature	255 to 270	°C	
Nozzle Temperature	240 to 275	°C	
Mold Temperature	60.0 to 100	°C	
Injection Pressure	60.0 to 90.0	MPa	
Injection Rate	Fast		
Holding Pressure	50.0 to 70.0	MPa	
Screw L/D Ratio	15.0:1.0 to 20.0:1.0		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

