

EvoSource™ ABS 4136

Acrylonitrile Butadiene Styrene

MBA Polymers

Message:

An easy flowing, post-consumer recycled acrylonitrile-butadiene-styrene copolymer for applications requiring increased impact strength. Available in standard grey (reference 70/15) and standard black (reference 90/04).

General Information	
Recycled Content	Yes
Features	Copolymer
	Good Flow
	Good Impact Resistance
Appearance	Black
	Grey
Forms	Pellets
Processing Method	Extrusion
	Injection Molding

Physical	Nominal Value	Unit	Test Method
Density	1.07	g/cm ³	Internal Method
Melt Mass-Flow Rate (MFR) (220°C/10.0 kg)	24	g/10 min	ISO 1133
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (23°C)	2350	MPa	ISO 527-2/1
Tensile Stress (Yield, 23°C)	40.0	MPa	ISO 527-2/50
Flexural Modulus (23°C)	2250	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	18	kJ/m ²	ISO 179/1eA
Notched Izod Impact Strength (23°C)	18	kJ/m ²	ISO 180/1A
Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature	88.0	°C	ISO 306/B50
Injection	Nominal Value	Unit	
Drying Temperature	80.0	°C	
Drying Time	3.0 to 4.0	hr	
Suggested Max Moisture	0.050 to 0.10	%	
Processing (Melt) Temp	210 to 250	°C	
Mold Temperature	40.0 to 60.0	°C	
Extrusion	Nominal Value	Unit	
Drying Temperature	80.0	°C	

Drying Time	3.0 to 4.0	hr
Suggested Max Moisture	0.050 to 0.10	%
Melt Temperature	200 to 220	°C

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

