

POLYLAC® PA-757G J08

Acrylonitrile Butadiene Styrene

CHI MEI CORPORATION

Message:

POLYLAC® PA-757G J08 is an Acrylonitrile Butadiene Styrene (ABS) product. It can be processed by injection molding and is available in Africa & Middle East, Asia Pacific, Europe, Latin America, or North America.

Characteristics include:

Flame Rated

RoHS Compliant

General Information			
UL YellowCard	E56070-565071		
RoHS Compliance	RoHS Compliant		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density (23°C)	1.04	g/cm ³	ISO 1183
Melt Volume-Flow Rate (MVR) (220°C/10.0 kg)	34.0	cm ³ /10min	ISO 1133
Hardness	Nominal Value	Unit	Test Method
Ball Indentation Hardness (H 358/30)	100	MPa	ISO 2039-1
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress			ISO 527-2/50
Yield	48.0	MPa	
Break	40.0	MPa	
Tensile Strain (Break)	39	%	ISO 527-2/50
Flexural Modulus ¹	1900	MPa	ISO 178
Flexural Stress ²	62.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			
--	17	kJ/m ²	ISO 179
--	14	kJ/m ²	ISO 179/2
Charpy Unnotched Impact Strength	No Break		ISO 179, ISO 179/2U
Notched Izod Impact Strength	16	kJ/m ²	ISO 180/1A
Unnotched Izod Impact Strength	No Break		ISO 180/1U
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			ISO 75-2/A
1.8 MPa, Unannealed	87.0	°C	
1.8 MPa, Annealed	98.0	°C	
Vicat Softening Temperature			
--	105	°C	ISO 306/A50
--	106	°C	ISO 306/A120
--	101	°C	ISO 306/B50

--	102	°C	ISO 306/B120
Flammability	Nominal Value	Test Method	
Flame Rating (1.59 mm)	HB	UL 94	
Injection	Nominal Value	Unit	
Drying Temperature	80.0 to 85.0	°C	
Drying Time	3.0 to 4.0	hr	
Rear Temperature	180 to 220	°C	
Middle Temperature	190 to 230	°C	
Front Temperature	190 to 230	°C	
Mold Temperature	80.0 to 120	°C	
Injection Pressure	4.90 to 5.88	MPa	
Holding Pressure	3.92 to 4.90	MPa	
Back Pressure	0.490 to 0.981	MPa	
NOTE			
1.	2.0 mm/min		
2.	2.0 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
 Phone: +86 13424755533
 Email: sales@su-jiao.com
 No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT