

ALCUDIA® HDPE R4805D1

High Density Polyethylene
REPSOL

Message:

ALCUDIA® R4805D1 is a low melt flow rate high density polyethylene with medium molecular weight distribution. It offers an optimum balance between mechanical and processing properties for production of tapes with high tensile strength at break. This product is specially formulated with a slip package.

TYPICAL APPLICATIONS

ALCUDIA® R4805D1 is designed for stretched tapes production based on blown film. It gives flexible tapes with high tenacity and low fibrillation tendency suitable for high speed textil lines:

Iso Mayer textile applications
Raschel knitted and woven fabrics.
Twines and ropes

Recommended melt temperature range from 210 to 230°C. Processing conditions should be optimised for each production line.

General Information			
Additive	slip agent		
Features	High tensile strength		
	smoothness		
	Workability, good		
	Low liquidity		
	Compliance of Food Exposure		
Uses	Medium wide molecular weight distribution		
	Twine		
	Strap		
	Rope		
	Fabric		
Agency Ratings	European food contact, not rated		
Processing Method	Blow film		
Physical	Nominal Value	Unit	Test Method
Density	0.948	g/cm³	ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	0.56	g/10 min	ISO 1133
Extrusion	Nominal Value	Unit	
Melt Temperature	180 - 230	°C	
Extrusion instructions			

Blow Up Ratio: 1.1 to 1.3

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

