

ULTEM™ ATX200F resin

Polyether Imide + PCE
SABIC Innovative Plastics

Message:
High flow Polyetherimide blend. ECO Conforming, UL94 V0 Listing. US FDA Food Contact compliant.

General Information			
UL YellowCard	E121562-221073		
Features	ECO Compliant		
	Food Contact Acceptable		
	High Flow		
Agency Ratings	EU Eco		
	FDA Food Contact, Unspecified Rating		
Processing Method	Injection Molding		
Multi-Point Data	Coefficient of Thermal Expansion vs. Temperature (ASTM E831)		
	Elastic Modulus vs Temperature (ASTM D4065)		
	Flexural DMA (ASTM D4065)		
	Tensile Fatigue		
	Tensile Stress vs. Strain (ASTM D638)		
	Thermal Conductivity vs. Temperature (ASTM E1530)		
	Viscosity vs. Shear Rate (ASTM D3835)		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.26	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (337°C/6.6 kg)	24	g/10 min	ASTM D1238
Molding Shrinkage - Flow (3.20 mm)	0.50 to 0.70	%	Internal Method
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ¹ (Yield)	96.5	MPa	ASTM D638
Tensile Elongation ² (Break)	70	%	ASTM D638
Flexural Modulus ³ (100 mm Span)	3170	MPa	ASTM D790
Flexural Strength ⁴ (Yield, 100 mm Span)	145	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	53	J/m	ASTM D256
Unnotched Izod Impact (23°C)	2100	J/m	ASTM D4812
Reverse Notch Izod Impact (3.20 mm)	2700	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed, 6.40 mm)	191	°C	ASTM D648

RTI Elec	115	°C	UL 746
RTI Imp	115	°C	UL 746
RTI Str	115	°C	UL 746
Electrical	Nominal Value	Test Method	
Comparative Tracking Index (CTI)	PLC 4	UL 746	
High Amp Arc Ignition (HAI)	PLC 4	UL 746	
Hot-wire Ignition (HWI)	PLC 0	UL 746	
Flammability	Nominal Value	Test Method	
Flame Rating		UL 94	
0.762 mm	V-2		
1.50 mm	V-0		
Injection	Nominal Value	Unit	
Drying Temperature	135	°C	
Drying Time	4.0 to 6.0	hr	
Drying Time, Maximum	10	hr	
Suggested Max Moisture	0.020	%	
Suggested Shot Size	40 to 60	%	
Rear Temperature	338 to 360	°C	
Middle Temperature	343 to 366	°C	
Front Temperature	349 to 371	°C	
Nozzle Temperature	349 to 371	°C	
Processing (Melt) Temp	349 to 371	°C	
Mold Temperature	135 to 163	°C	
Back Pressure	0.345 to 0.689	MPa	
Screw Speed	40 to 70	rpm	
Vent Depth	0.025 to 0.076	mm	
NOTE			
1.	Type I, 5.0 mm/min		
2.	Type I, 5.0 mm/min		
3.	2.6 mm/min		
4.	2.6 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT