

NILENE® E K20T

Polypropylene Copolymer

Taro Plast S.p.A.

Message:

Polypropylene copolymer 20% talcum filled, flame rating UL94 HB.

General Information			
UL YellowCard	E143048-100035146		
Filler / Reinforcement	Talc filler, 20% filler by weight		
Features	Copolymer		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Density	1.05	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	10	g/10 min	ISO 1133
Molding Shrinkage			Internal method
Vertical flow direction	1.1	%	Internal method
Flow direction	1.1	%	Internal method
Water Absorption (23°C, 24 hr)	0.050	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Yield)	30.0	MPa	ISO 527-2/50
Tensile Strain (Break)	32	%	ISO 527-2/50
Flexural Modulus ¹	1900	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	5.2	kJ/m ²	ISO 179/1eA
Notched Izod Impact			ASTM D256
-20°C	30	J/m	ASTM D256
0°C	40	J/m	ASTM D256
23°C	55	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, not annealed	130	°C	ISO 75-2/B
1.8 MPa, not annealed	60.0	°C	ISO 75-2/A
Vicat Softening Temperature			
--	152	°C	ISO 306/A50
--	80.0	°C	ISO 306/B50
CLTE - Flow	6.0E-5	cm/cm/°C	ISO 11359-2
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.0E+17	ohms · cm	IEC 60093
Comparative Tracking Index (Solution A)	> 600	V	IEC 60112

Flammability	Nominal Value	Unit	Test Method
Burning Rate ² (2.00 mm)	< 100	mm/min	ISO 3795
Flame Rating (1.60 mm)	HB		UL 94
Glow Wire Flammability Index (1.60 mm)	650	°C	IEC 60695-2-12
Additional Information	Nominal Value	Unit	Test Method
Reinforcement Content ³ (600°C)	20	%	ISO 3451
Injection	Nominal Value	Unit	
Processing (Melt) Temp	190 - 230	°C	
Mold Temperature	30.0 - 50.0	°C	
Injection Rate	Moderate		
Injection instructions			
Pre-heat Temperature: 70 to 80°CPre-heat Time: 1 hr			
NOTE			
1.	1.0 mm/min		
2.	US FMVSS302		
3.	1 hr		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

