

Plenco 06401 (Compression)

Phenolic

Plastics Engineering Co.

Message:

PLENCO 06401 is a glass fiber and mineral filled two-stage phenolic molding compound. UL recognized under component file E40654. 06401 is available in black.

General Information			
UL YellowCard	E40654-231621		
Filler / Reinforcement	Glass fiber reinforced material Mineral filler		
UL File Number	E40654		
Appearance	Black		
Forms	Particles		
Processing Method	Compression molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.75	g/cm ³	ASTM D792
Apparent Density	0.74	g/cm ³	ASTM D1895
Molding Shrinkage - Flow	0.15	%	ASTM D955
Water Absorption (24 hr)	0.070	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (E-Scale)	97		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	14600	MPa	ASTM D638
Tensile Strength	69.0	MPa	ASTM D638
Tensile Elongation (Break)	0.60	%	ASTM D638
Flexural Modulus	13100	MPa	ASTM D790
Flexural Strength	119	MPa	ASTM D790
Compressive Strength	253	MPa	ASTM D695
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength	39.6	J/m	ASTM D256
Notched Izod Impact	39	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	227	°C	ASTM D648
Continuous Use Temperature	226	°C	ASTM D794
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	3.4E+12	ohms · cm	ASTM D257
Dielectric Strength ¹	15	kV/mm	ASTM D149
Dielectric Constant (1 MHz)	5.20		ASTM D150

Dissipation Factor (1 MHz)	0.025		ASTM D150
Arc Resistance	96.0	sec	ASTM D495
Comparative Tracking Index (CTI)	175	V	UL 746
Flammability	Nominal Value	Unit	Test Method
Flame Rating (1.50 mm)	V-0		UL 94
Additional Information			
The value listed as Comparative Tracking Index, UL 746 was tested according to ASTM D3638.The value listed as Mold Shrink, Linear-Flow, ASTM D955 was tested according to the ASTM D6289 standard.Post Shrinkage, ASTM D6289, 72hr, 120°C: 0.05%Drop Ball Impact, PLENCO Method: 275 J/m			
Injection	Nominal Value	Unit	
Mold Temperature	165 - 182	°C	
Back Pressure	0.300	MPa	
Screw Speed	< 60	rpm	
Injection instructions			
Mold Close Time: 3-8 sec			
NOTE			
1.	Method A (short time)		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material


Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT