

# MTM® 85S

Phenolic

Cytec Industries Inc.

## Message:

MTM® 85S is a 160°C (275°F) curing, phenolic prepreg system optimised for high pressure compression moulding.

MTM85S can be supplied on a range of fabrics and fibres, but typically with nylon, aramid and glass for helmets and other armour applications.

General Information	
Filler / Reinforcement	Aramid Fiber
	Glass Fiber
	Nylon Fiber
Features	Heat Cure
Uses	Protective Coverings
Forms	Fabric
	Fiber
Processing Method	Compression Molding

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

## Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

