## Maxxam™ PPC-30T UV EXT 1148

# Polypropylene Copolymer PolyOne Corporation

#### Message:

PolyOne's Maxxam™ family of polypropylene- and polyethylene-based products covers a wide range of applications, markets and performance requirements. Standard grades are compounded with calcium carbonate, glass and talc to provide a desired balance of properties including stiffness, durability, impact resistance and heat resistance. Custom grades are available with features such as UV stabilizers, heat stabilizers, custom color, high impact, etc.

| General Information  |                           |       |             |
|--|---------------------------|-------|-------------|
| Filler / Reinforcement   | Talc,30% Filler by Weight |       |             |
| Additive   | UV Stabilizer             |       |             |
| Features   | Copolymer                 |       |             |
|  | General Purpose           |       |             |
|  | Good UV Resistance        |       |             |
|  |                           |       |             |
| Uses   | Automotive Applications   |       |             |
|  | Construction Applications |       |             |
|  | Consumer Applications     |       |             |
|  | General Purpose           |       |             |
|  | Industrial Applications   |       |             |
|  |                           |       |             |
| Appearance   | Natural Color             |       |             |
| Forms  | Pellets                   |       |             |
| Processing Method  | Injection Molding         |       |             |
| Physical   | Nominal Value             | Unit  | Test Method |
| Specific Gravity   | 1.14                      | g/cm³ | ASTM D792   |
| Molding Shrinkage - Flow   | 0.60 to 1.0               | %     | ASTM D955   |
| Mechanical   | Nominal Value             | Unit  | Test Method |
| Tensile Strength <sup>1</sup> (Yield)                                | 24.1                      | MPa   | ASTM D638   |
| Tensile Elongation <sup>2</sup> (Break)                              | 40                        | %     | ASTM D638   |
| Flexural Modulus   | 2340                      | MPa   | ASTM D790   |
| Flexural Strength  | 38.6                      | MPa   | ASTM D790   |
| Impact   | Nominal Value             | Unit  | Test Method |
| Notched Izod Impact (23°C, 3.18 mm, Injection Molded)                | 48                        | J/m   | ASTM D256A  |
| Thermal  | Nominal Value             | Unit  | Test Method |
| Deflection Temperature Under Load (0.45<br>MPa, Unannealed, 3.18 mm) | 118                       | °C    | ASTM D648   |
| Injection  | Nominal Value             | Unit  |             |
| Mold Temperature   | 16.0 to 50.0              | °C    |             |
| NOTE   |                           |       |             |

| 1. Type I, 51 mm/min |
|----------------------|
|----------------------|

Type I, 51 mm/min

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

2.

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

