Europrene® N OZO 7028

Polyvinyl Chloride + NBR

Versalis S.p.A.

Message:

Europrene[®] N OZO 7028 is a blend of acrylonitrile-butadiene copolymer and polyvinyl chloride in the ratio 70/30. The fluxing stage is fully achieved during the mechanical mixing thus providing outstanding resistance against ozone and good oil, abrasion and fire resistance together with an excellent processability.

Europrene® N OZO 7028 is characterised by an excellent processability in internal and open mixers, high resistance to oils and outstanding fire resistance. This grade represents the best compromise between ozone resistance and low temperature performances. Particularly suitable for extrusion and injection moulding applications, this grade could be vulcanized with sulphur based systems or with peroxides.

Conveyor belts, safety shoe soles, cable jackets, insulating hoses, industrial and automotive hoses, flooring, fire hoses and all applications where fire and ozone resistance are required together with good flexibility at low temperature.

General Information			
Features	Flame Retardant		
	Good Abrasion Resistance		
	Good Processability		
	Low Temperature Flexibility		
	Low Temperature Resistant		
	Oil Resistant		
	Ozone Resistant		
	Vulcanizable		
Uses	Automotive Applications		
	Belts/Belt Repair		
	Cable Jacketing		
	Conveyor Parts		
	Flooring Maintenance/Repair		
	Footwear		
	Hose		
	Industrial Applications		
Forms	Bale		
Processing Method	Extrusion		
	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Mooney Viscosity (ML 1+4, 100°C)	75	MU	ASTM D1646
Acrylonitrile Content	19.5	wt%	ASTM D3533
Ash Content	< 0.5	wt%	ASTM D5667
Volatile Matter	< 1.0	wt%	ASTM D5668
NBR/PVC Ratio - wt/wt	70/30		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

