

GAPEX® RPP25DZ09OR

Polypropylene Homopolymer

Ferro Corporation

Message:

GAPEX®RPP25DZ09OR is a polypropylene homopolymer (PP Homopoly) material containing 25% glass beads. This product is available in North America, Africa and the Middle East, Latin America, Europe or Asia Pacific. GAPEX®The main characteristics of the RPP25DZ09OR are: homopolymer.

General Information			
Filler / Reinforcement	Glass beads, 25% filler by weight		
Features	Homopolymer		
Forms	Particle		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.09	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	9.0	g/10 min	ASTM D1238
Molding Shrinkage			ASTM D955
Flow	0.80	%	ASTM D955
Transverse flow	1.3	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield, 23°C)	42.1	MPa	ASTM D638
Tensile Elongation (Break, 23°C)	3.0	%	ASTM D638
Flexural Modulus			ASTM D790
1% secant: 23°C	2900	MPa	ASTM D790
Tangent: 23°C	3170	MPa	ASTM D790
Flexural Strength (Yield, 23°C)	66.9	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	32	J/m	ASTM D256
Unnotched Izod Impact (23°C)	180	J/m	ASTM D256
Dart Drop Impact	0.226	J	ASTM D5420
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, not annealed	154	°C	ASTM D648
1.8 MPa, not annealed	121	°C	ASTM D648
Additional Information			
Filler Content, ASTM D2584: 25%			
Injection	Nominal Value	Unit	
Drying Temperature	71.1 - 82.2	°C	
Drying Time	2.0 - 4.0	hr	
Rear Temperature	221 - 238	°C	
Middle Temperature	227 - 243	°C	
Front Temperature	232 - 260	°C	

Nozzle Temperature	232 - 260	°C
Processing (Melt) Temp	221 - 238	°C
Mold Temperature	37.8 - 65.6	°C
Injection Rate	Slow-Moderate	
Back Pressure	0.138 - 0.345	MPa
Cushion	5.08 - 12.7	mm

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

