Hostacom TRC 452N G72758

Polypropylene Copolymer LyondellBasell Industries

Message:

Hostacom TRC 452N G72758 is a 20% talc filled PP copolymer, with excellent impact/stiffness balance and good flowability and good scratch resistance, outstanding blooming resistance at elevated temperatures and good antistatic behavior. Product is available as a customized color matched, pellet form. This grade is delivered in G72758 color version.

This grade is not intended for medical, pharmaceutical, food and drinking water applications.

General Information			
Filler / Reinforcement	Talc filler, 20% filler by weight		
Features	Low blur phenomenon		
	Rigid, good		
	Copolymer		
	Antistatic property		
	Impact resistance, good		
	Good liquidity		
	Scratch resistance		
Annonen es	Available colors		
Appearance			
Forms	Particle		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Density (23°C)	1.04	g/cm³	ISO 1183/A
Melt Mass-Flow Rate (MFR) (230°C/2.16			
kg)	18	g/10 min	ISO 1133
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Yield, 23°C)	20.0	MPa	ISO 527-2
Flexural Modulus ¹ (23°C)	1900	МРа	ISO 178/A
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
-30°C	4.0	kJ/m²	ISO 179/1eA
23°C	30	kJ/m²	ISO 179/1eA
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, not annealed	101	°C	ISO 75-2/B
1.8 MPa, not annealed	54.0	°C	ISO 75-2/A
NOTE			
1.	1.0 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

