

Manner Flexible PVC X3564

Flexible Polyvinyl Chloride

Manner Plastics, L.P.

Message:

Lead-free profile extrusion compound. This product complies with the European Union Restriction on Hazardous Substances (RoHS) directive.

General Information			
Features	Low (to None) Lead Content		
Uses	Profiles		
RoHS Compliance	RoHS Compliant		
Processing Method	Profile Extrusion		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.30 to 1.34	g/cm ³	ASTM D792
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A)	85		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength			ASTM D638
3.18 mm	16.3	MPa	
100% Strain,3.18 mm	7.97	MPa	
Tensile Elongation (Break, 3.18 mm)	380	%	ASTM D638

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material


Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT