

Bynel® 41E710

Linear Low Density Polyethylene
DuPont Packaging & Industrial Polymers

Message:

BYNEL® Series 4100 resins are anhydride-modified, linear low-density polyethylene (LLDPE) resins. All 4100 series resins are available in pellet form for use in conventional extrusion and coextrusion equipment designed to process polyethylene (PE) resins.

BYNEL 41E710 is a grade with a higher level of anhydride modification, and is mainly intended for use as a component in a blend with other polyolefin resins. It is not intended for extrusion in its pure form in typical extrusions or coextrusions.

BYNEL 4100 series resins adhere to a variety of materials. They are most often used to adhere to EVOH, polyamide, PE and ethylene copolymers.

Series 4100 resins can be used in coextrusion processes including:

- blown film
- cast film/sheet
- blow molding
- melt and solid phase thermoforming
- sheet and tubing

LLDPE resins are known for their temperature resistance, clarity and toughness.

These physical properties make the 4100 series resins work well in applications such as:

- boil-in-bag structures
- blow molded containers in which drop strength is important
- bag-in-box films
- film where LLDPE is the heat seal layer.

General Information			
Features	Good adhesion		
Uses	Films		
	Blow molding applications		
	Pipe fittings		
	Mixing		
	cast film		
	Sheet		
	Container		
	Adhesive		
Agency Ratings	FDA 21 CFR 175.105		
Forms	Particle		
Processing Method	Solid Phase Press. Form. Thermoforming		
	Blow molding		
	Co-extrusion molding		
	Extrusion		
	Thermoforming		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.910	g/cm³	ASTM D792, ISO 1183
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	2.7	g/10 min	ASTM D1238, ISO 1133
Thermal	Nominal Value	Unit	Test Method

Vicat Softening Temperature	103	°C	ASTM D1525, ISO 306
Melting Temperature (DSC)	115	°C	ASTM D3418, ISO 3146
Freezing Point			
--	98	°C	ISO 3146
--	98	°C	ASTM D3418
Extrusion	Nominal Value	Unit	
Cylinder Zone 1 Temp.	160	°C	
Cylinder Zone 2 Temp.	185	°C	
Cylinder Zone 3 Temp.	235	°C	
Cylinder Zone 4 Temp.	235	°C	
Cylinder Zone 5 Temp.	235	°C	
Adapter Temperature	235	°C	
Melt Temperature	< 260	°C	
Die Temperature	235	°C	

Extrusion instructions

Processing conditions shown are for coextrusion with EVOH. Processing conditions for coextrusion with nylon: Zone 1: 160°C Zone 2: 185°C Zone 3: 235°C Zone 4: 260°C Zone 5: 260°C Adapter: 260°C Die: 260°C

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co., Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

