

Sarlink® TPE AB-1238DN

Thermoplastic Elastomer

Teknor Apex Company

Message:

Sarlink® TPE AB-1238DN is a thermoplastic elastomer (TPE) material. This product is available in North America, Africa and the Middle East, Latin America, Europe or Asia Pacific. The processing method is injection molding.

Sarlink® The typical application field of TPE AB-1238DN is: automobile industry

General Information			
Uses	Car interior parts		
Appearance	Translucent		
Forms	Particle		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.968	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	10	g/10 min	ASTM D1238
Molding Shrinkage			ISO 2577
Flow	1.2	%	ISO 2577
Transverse flow	1.2	%	ISO 2577
Water Absorption			ISO 62
Saturated, 23°C	0.023	%	ISO 62
Equilibrium, 23°C, 50% RH	8.0E-3	%	ISO 62
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore D, 10 sec)	44		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus			ISO 527-2
23°C	138	MPa	ISO 527-2
85°C	12.0	MPa	ISO 527-2
Tensile Stress			ISO 527-2
Fracture, -35°C	25.6	MPa	ISO 527-2
Fracture, 23°C	21.7	MPa	ISO 527-2
Fracture, 85°C	5.50	MPa	ISO 527-2
100% strain, -35 c	16.5	MPa	ISO 527-2
100% strain, 23°C	8.41	MPa	ISO 527-2
100% strain, 85°C	4.30	MPa	ISO 527-2
Tensile Strain			ISO 527-2
Fracture, -35°C	480	%	ISO 527-2
Fracture, 23°C	690	%	ISO 527-2
Fracture, 85°C	> 500	%	ISO 527-2
Flexural Modulus			ISO 178

23°C	205	MPa	ISO 178
85°C	34.3	MPa	ISO 178
Elastomers	Nominal Value	Unit	Test Method
Tear Strength			ISO 34-1
-35°C	130	kN/m	ISO 34-1
23°C	74	kN/m	ISO 34-1
85°C	40	kN/m	ISO 34-1
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (0.45 MPa, Annealed)	43.9	°C	ISO 75-2/B
Glass Transition Temperature	-60.0	°C	DSC
Melting Temperature (DSC)	159	°C	ISO 3146
Additional Information			
火灾水平蔓延速率= 3.3 英寸/分钟(83 毫米/分钟)雾化,3小时,100 C箱内展开 (-35C) = 合格			
Injection	Nominal Value	Unit	
Rear Temperature	199 - 210	°C	
Middle Temperature	204 - 216	°C	
Front Temperature	210 - 221	°C	
Nozzle Temperature	216 - 227	°C	
Processing (Melt) Temp	216 - 227	°C	
Mold Temperature	35.0 - 65.6	°C	
Injection Pressure	1.38 - 6.89	MPa	
Injection Rate	Fast		
Back Pressure	0.172 - 0.862	MPa	
Screw Speed	50 - 120	rpm	
Cushion	3.81 - 25.4	mm	
Injection instructions			
无需干燥.但如果湿度过大,则将粒料在150°F (65°C)的温度下干燥2-4小时.			
Extrusion	Nominal Value	Unit	
Cylinder Zone 1 Temp.	193 - 204	°C	
Cylinder Zone 2 Temp.	199 - 210	°C	
Cylinder Zone 3 Temp.	204 - 216	°C	
Cylinder Zone 5 Temp.	210 - 221	°C	
Die Temperature	216 - 227	°C	
Extrusion instructions			
螺杆转速30 - 100 rpm			

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

